

Razin™ Engineering Plastics		Quality Management System	
Form Code:TE-F01.00	No.:P121 TR30	Product Information	

Razalen® P121 TR30

Razalen P121 TR30 is a general purpose injection grade black color impact copolymer polypropylene reinforced with 30% Talc. It combines good toughness as well as excellent processability chemical and fatigue resistance.

Properties	Test Method	Unit	Value
Physical			
Density	ASTM D 792	g/cm ³	1.15
MFR(230°C, 2.16 kg)	ASTM D 1238	g/10 min	9
Linear Mold Shrinkage	ASTM D 955	%	1.0

Mechanical			
Tensile Strength, Yield	ASTM D 638	MPa	26
Elongation at Break	ASTM D 638	%	20
Flexural Strength	ASTM D 790	MPa	46
Flexural Modulus	ASTM D 790	MPa	2500
Izod Impact, Notched			
@ 23 °C	ASTM D 256	J/m	40
@ -30 °C			-

Thermal			
Deflection Temperature Under Load			
@ 0.46 MPa	ASTM D 648	°C	-
@ 1.8 MPa			73
Vicat Softening point	ASTM D 1525	°C	-

Processing						
Drying:						
	Drying Time:	1.0 – 2.0 hr		Drying Temperature:	80 - 100 °C	
Injection Molding:						
Item	Rear Temp (°C)	Middle Temp (°C)	Front Temp (°C)	Melt Temp (°C)	Mold Temp (°C)	Inj. Pressure (Mpa)
Min	180	190	200	210	30	40
Max	200	210	220	230	80	130

The data contained in this publication are based on our current knowledge and experience. In view of the many actors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose.